

SD Coatings Limited

Product Data Sheet

Weatherguard CB Stipple

Usage

For Exterior use on soft wood, hardwood, hardwood ply, silica boards, masonry, concrete render and brickwork.

Suitable Substrates and Preparation

Softwood, hardwood, hardwood ply or silica board primed with any S D Coatings Limited primer, masonry, sealed concrete render and sealed brickwork.

Application Details

Roller Apply evenly using a well loaded texture or Irish roller

Cleaner Materials and equipment should be washed in water. Skin should be washed in hot water and soap.

Spread Rate (Typical) 1 Square Metres Per Litre at 80 Microns wet

Film Thickness per coat

	Dry	Wet
Minimum	50 microns	80 microns
Maximum	166 microns	270 microns

Drying and Recoating

Approximate Drying Times at 50 microns.

Substrate Temperature	Surface Dry	Fully Dry
10 degrees Celsius	6 hours	12 hours
20 degrees Celsius	3 hours	8 hours

Environmental Conditions

Upon application the air temperature must be above 5 degrees Celsius and the surface temperature 5 degrees Celsius above dew point and the relative humidity below 80 %.

It should be noted that in wet damp conditions the drying times will be extended and in these conditions the use of moisture metres is recommended.

CB Product Data Sheets

Storage and Handling

Storage	Store in an enclosed environment with a temperature range of 5 – 25 degrees Celsius
Shelf life	Provided it is stored as above in unopened containers the product has an expected shelf life of 6 months from date of manufacture.

Product Information

Composition	Based on waterborne, high solids, colloid stabilised, styrene acrylic co-polymer dispersion, with suitable pigments and extenders.
Supply Viscosity	75 to 85 poise at 20 degrees Celsius.
Flash Point	None

Safety Precautions

NON – FLAMMABLE: Water Based Product

Disposal Considerations

Waste Product should not be discharged directly into drains or waterways without treatment. Disposal of product and packaging should always comply with local and national regulations.

EU Waste code – No waste code number available

Ecological Information

Degradation /elimination	DOC elimination after 2 days
Bioaccumulation	No evidence for bioaccumulation
Ecotoxic effects	The product is not classified as dangerous for the environment

Health and Safety Sheet: SDC 250607CB

The information given herein is given as to be correct to the best of our knowledge but without warranty.

S D Coatings Limited.
Unit 9 Hexthorpe Trading Park, Hexthorpe Doncaster, DN4 0EJ
Tel: 01302 325758
Fax: 01302 360439
Email: sales@sdcoatings.co.uk
www.sdcoatings.co.uk

